

ExxonMobil HDPE

HPA 020

Blow Molding Resin

Description

HPA 020

HPA 020 is a high molecular weight HDPE resin, characterized by an excellent balance of rigidity, ESCR and impact strength.

Applications

- large parts & containers (20 to 100 I) for non - food end uses
- non pressure pipes for use in construction industry

| Additive Package | Thermal Stabilizer |
|------------------|--------------------|
|------------------|--------------------|

| 111 77 020 | 7.020 | | JO | |
|-------------------------------|-------------------|-------------------------|--------|--|
| Resin Properties | Test Based On | Typical Value / Unit | | |
| Melt Index (21.6 kg, 47.6 lb) | ASTM D 1238 | 9 g/10 min | | |
| Melt Index (2.16 kg, 4.76 lb) | ASTM D 1238 | 0.07 g/10 min | | |
| Density | ExxonMobil Method | 0.952 g/cm ³ | | |
| Vicat Softening Point | ASTM D 1525 | 129 °C | 257 °F | |

Molded Properties

| Tensile Strength at Yield ¹ | ASTM D 638 | 26 MPa | 3750 psi |
|--|-------------|----------------------|----------------------------|
| Tensile Strength at Break ¹ | ASTM D 638 | > 17 MPa | > 2450 psi |
| Elongation at Break ¹ | ASTM D 638 | > 450 % | |
| 1% Secant Modulus ² | ASTM D 638 | 850 MPa | 123500 psi |
| IZOD Impact | ASTM D 256 | 38 kJ/m ² | 18.1 ft-lb/in ² |
| Shore Hardness, D | ASTM D 2240 | 63 | |
| Environmental Stress Crack Resistance ³ | ASTM D 1693 | > 300 hrs | |
| Environmental Stress Crack Resistance ⁴ | ASTM D 1693 | > 600 hrs | |

The molded properties have been measured on compression molded sheets, prepared according to ASTM D4703.

HPA 020 is not to be used for food contact applications.

⁽¹⁾ Specimen type T4 / thickness 3 mm (118 mil); speed of testing 50 mm/min (1970 mil/min). (2) Specimen type T4 / thickness 3 mm (118 mil); speed of testing 5 mm/min (197 mil/min). (3) Conditions B, F50, 10 % Igepal

⁽⁴⁾ Conditions B, F50, 100 % Igepal